

PRODUCT DATA SHEET

PRO LIQUID GAS BARRIER

Product Code: DMS405



GROUND GAS
MEMBRANES

info@deltamembranes.com

www.deltamembranes.com

01992 523 523

PRO LGB is a ready for use specialist styrene butadiene latex based liquid applied gas membrane.

It offers a simple, continuous passive gas prevention barrier against the ingress of Methane, Carbon Dioxide, Radon, Ground Gas, VOC, air & moisture into buildings. PRO LGB also acts as a waterproofing membrane complying with the requirement C2 and C4 schedule 1 of the Building Regulations 1991 for England and Wales.



BENEFITS

- Suitable for Hydrocarbons, Methane (CH₄), Carbon Dioxide (CO₂), Radon (Rn), Volatile Organic Compound (VOCs)
- Suitable for new and existing structures
- 3rd Party Accredited/Independently tested
- Acts as a Damp Proof Membrane
- Complies with BRE211:2015 and BS8485:2015
- Liquid Gas Membrane can be used for providing damp proofing, gas proofing or waterproofing to a range of applications.



SPECIFICATION

- BS8485:2015+A1:2019
- J30 Liquid Applied Tanking/Damp Proofing



ASSOCIATED PRODUCTS

- GGM R1
- GGM M1
- Delta Cavity Drainage System
- Koster Repair Mortar
- Koster Polysil TG500
- Koster SB Bonding
- Flexi Tape

PRODUCT DATA SHEET

PRO LIQUID GAS BARRIER

Product Code: DMS405

PROPERTIES

PRO LGB can be used to protect most building surfaces from the effect of liquid and water vapour, carbonation and as a gas barrier to prevent the ingress of Methane, Carbon Dioxide and Radon. As the product is a barrier to moisture it can be used as a DPM on floors and walls.

COVERAGE

PRO LGB may be applied by brush, roller or airless spray. A minimum dry coated thickness of 1.0mm is needed to provide a gas barrier. To achieve 1.0mm thickness, a total of 2kg/m² is required, therefore a 15kg tub will cover an area of 7.5m².

APPLICATION

The background surface should be smooth or have a light even texture, and masonry should be flush pointed and defects in the surfaces made good prior to application. The surface should be clean, sound and free of dust, loose material or free surface water. The PRO LGB should not be applied in wet conditions or where inclement weather is expected before the membrane has dried. The membrane should not be applied in temperatures below 7°C. Where multiple coats are applied, it is recommended that the coats are applied at right angles to each other. Before application of secondary coats it is necessary to let the first coat become touch dry. The time required to reach touch dry condition will vary dependant on site conditions within the working area, but will typically be in the order of 1-2 hours in favourable conditions. It is preferable that secondary coats are applied within 24 hours.

HANDLING

Material is supplied in tubs of 15kg weight. Appropriate care must be taken with handling. Clean tools with water immediately after use.

STORAGE

Store tub in conditions between 5°C and 30°C; Shelf life 12 months unopened.

JOINTING/SEALING/COMPATABILITY

PRO LGB is compatible with loose laid membranes supplied by Delta Membrane Systems Ltd, such as PRO M1, PRO R1, MS Membranes, and PRO TITAN.

Head Office:

Delta House, Merlin Way, North Weald, Epping, Essex, CM16 6HR
01992 523 523 | info@deltamembranes.com | www.deltamembranes.com

DMSPDS2020

PRODUCT DATA SHEET

PRO LIQUID GAS BARRIER

Product Code: DMS405

PRO LIQUID GAS BARRIER

Characteristic	Test Method	Unit	Liquid Gas Barrier
PHYSICAL PROPERTIES			
Applied Thickness			>1.0
Form Supplied			Viscous Liquid
Pack Size			15kg
Colour			Red
Chemical Composition			Advanced SBS with speciality additives
HYDRAULIC PROPERTIES			
Water tightness	EN 1296, EN 1367, EN 1928		PASS
PHYSICAL PROPERTIES			
Methane Permeability	BS EN ISO 15105-1	ml/m ² /day/atm	33.00
Radon Permeability	Saarland University	mm	>1.0mm applied thickness provides a complete barrier to Radon

Head Office:

Delta House, Merlin Way, North Weald, Epping, Essex, CM16 6HR
01992 523 523 | info@deltamembranes.com | www.deltamembranes.com

DMSPDS2020