

Certificate of Test

Page 1 of 2

Title: Delta MS-500 Membrane

**Determination of Carbon Dioxide
Gas Permeability**

Certificate of Test Number: 19022

Customer's Name & Address:

DELTA Membrane Systems Ltd
Delta House, Merlin Way,
North Weald,
Epping,
Essex
CM16 6HR

Our Ref: N950/TR0006

VTC Job No: 3SQ0 – 1.345.01


Your Ref: P.O. #012689 dated 07-Aug-13

Date: 20 January 2014

Date samples received: 03 September 2013

Samples received from: Client

Sample No: 148543 – 148544

Written by: 
D Thompson (position: Engineer)

Authorised by: 
N McDonald (position: Principal Engineer)

VINCI Technology Centre UK Limited

01525 859000

info@technology-centre.co.uk

www.technology-centre.co.uk

Stanbridge Road, Leighton Buzzard, Bedfordshire, LU7 4QH

Registered office, Watford, England. Registered No. 05640885

This Certificate of Test is copyright. Reproduction of the whole or any part thereof must not be made without the express permission of VINCI Technology Centre UK Limited.

This Certificate of Test and the results shown are based upon the information, drawings, samples and tests referred to herein.

VINCI Technology Centre UK Limited accepts no liability for any damages, charges, costs (including, but not limited to, legal costs) or expenses in respect of or in relation to any damage to any property or other loss (save for death or personal injury occasioned by reason of any negligence on the part of VINCI Technology Centre UK Limited) whatsoever arising directly or indirectly from the use of this Certificate of Test, or the use of any goods or materials referred to in this Certificate of Test.

1. INTRODUCTION

This certificate of test describes the Carbon Dioxide gas permeability testing carried out at the request of Delta Membrane Systems Ltd on 13 January 2014 at VINCI Technology Centre (VTC), Leighton Buzzard.

The test was carried out in accordance with In-House Test Procedure TP950/05/13569 Issue 1 and "Rilem Report 12, Performance Criteria for Concrete Durability, E & FN Spon, London, UK pp 226 – 230".

2. SAMPLE DESCRIPTION

Technology Centre received 2no. A4 sized sheets of Delta MS-500 membrane. One sheet of Delta MS-500 membrane, Plain (TC Ref 148543) and one sheet of Delta MS-500 membrane, Jointed (TC Ref 148544). The membranes were given unique TC sample numbers for reference purposes only.

3. TEST PROCEDURE

An approximately 95mm diameter sized specimen was cut from each sheet (the jointed membrane incorporated the joint within the test area), and was sealed in a circular steel rig such that both faces were exposed. Carbon Dioxide gas at approximately 20kPa above atmospheric pressure was passed over one face of the membrane, and any gas flow passing through the sample was determined via a gas bubble-meter.

4. TEST RESULTS

The results for the testing are contained in Table 1 below.

CARBON DIOXIDE GAS PERMEABILITY RESULTS

Table 1

Client Reference	TC Ref	Specimen Thickness (m)	Exposed Area (m ²)	CO ₂ Gas Permeability (K _{gas}) (m/s)
Delta MS-500 Membrane (Plain)	148543	4.000 x10 ⁻⁴	5.816 x10 ⁻³	5.96 x10 ⁻¹¹
Delta MS-500 Membrane (Jointed)	148544	1.555 x10 ^{-3*}	5.926 x10 ⁻³	1.03 x10 ⁻⁹

Date of test: 13 January 2014

* Thickness based upon average of 4no. readings : two on unjointed & two on jointed areas.

5. SPECIFICATION

The permeability specification for non-geological barriers is as follows:

For inert waste: K_{gas} <1.00 x10⁻⁷ m/s.

Taken from Council Directive 193/31/EC dated 04/1999.

END OF CERTIFICATE

APPROVED