

Certificate of Test

Page 1 of 2

Title: Delta MS-20 Membrane

**Determination of Methane /
Radon Gas Permeability**

Certificate of Test Number: 19025

Customer's Name & Address:

DELTA Membrane Systems Ltd
Delta House, Merlin Way,
North Weald,
Epping,
Essex
CM16 6HR

Our Ref: N950/TR0006

VTC Job No: 3SQ0 – 1.345.01

Your Ref: P.O. #012689 dated 07-Aug-13

Date: 20 January 2014

Date samples received: 03 September 2013

Samples received from: Client

Sample No: 148545 – 148546

Written by: 
D Thompson (position: Engineer)

Authorised by: 
N McDonald (position: Principal Engineer)

VINCI Technology Centre UK Limited

01525 859000

info@technology-centre.co.uk

www.technology-centre.co.uk

Stanbridge Road, Leighton Buzzard, Bedfordshire, LU7 4QH

Registered office, Watford, England. Registered No. 05640885

This Certificate of Test is copyright. Reproduction of the whole or any part thereof must not be made without the express permission of VINCI Technology Centre UK Limited.

This Certificate of Test and the results shown are based upon the information, drawings, samples and tests referred to herein.

VINCI Technology Centre UK Limited accepts no liability for any damages, charges, costs (including, but not limited to, legal costs) or expenses in respect of or in relation to any damage to any property or other loss (save for death or personal injury occasioned by reason of any negligence on the part of VINCI Technology Centre UK Limited) whatsoever arising directly or indirectly from the use of this Certificate of Test, or the use of any goods or materials referred to in this Certificate of Test.

TC-N950-TEMP-055(B)

TECHNOLOGY 
CENTRE

1. INTRODUCTION

This certificate of test describes the methane permeability testing carried out at the request of Delta Membrane Systems Ltd on 16 January 2014 at VINCI Technology Centre (VTC), Leighton Buzzard.

The test was carried out in accordance with In-House Test Procedure TP950/05/13569 Issue 1 and "Rilem Report 12, Performance Criteria for Concrete Durability, E & FN Spon, London, UK pp 226 – 230".

2. SAMPLE DESCRIPTION

Technology Centre received 2no. A4 sized sheets of Delta MS-20 membrane. One sheet of Delta MS-20 membrane, Plain (TC Ref 148545) and one sheet of Delta MS-20 membrane, Jointed (TC Ref 148546). The membranes were given unique TC sample numbers for reference purposes only.

3. TEST PROCEDURE

An approximately 95mm diameter sized specimen was cut from each sheet (the jointed membrane incorporated the joint within the test area), and was sealed in a circular steel rig such that both faces were exposed. Methane gas at approximately 23kPa above atmospheric pressure was passed over one face of the membrane, and any gas flow passing through the sample was determined via a gas bubble-meter.

4. TEST RESULTS

The results for the testing are contained in Table 1 below.

METHANE / RADON GAS PERMEABILITY RESULTS

Table 1

| Client Reference | TC Ref | Specimen Thickness (m) | Exposed Area (m ²) | Methane Gas Permeability (K _{gas}) (m/s) | Radon Gas Permeability (K _{gas}) (m/s) |
|--------------------------------|--------|--------------------------|--------------------------------|--|--|
| Delta MS-20 Membrane (Plain) | 148545 | 8.000 x10 ⁻⁴ | 6.783 x10 ⁻³ | 3.32 x10 ⁻¹¹ | 1.27 x10 ⁻¹¹ |
| Delta MS-20 Membrane (Jointed) | 148546 | 2.185 x10 ^{-3*} | 5.803 x10 ⁻³ | 8.33 x10 ⁻¹⁰ | 3.18 x10 ⁻¹⁰ |

Date of test: 16 January 2015

* Thickness based upon average of 4no. readings – two on unjointed, two on jointed areas.
Note: The Methane gas permeability gained is used to determine the Radon gas permeability

5. SPECIFICATION

The permeability specification for non-geological barriers is as follows:

For inert waste: K_{gas} <1.00 x10⁻⁷ m/s.

Taken from Council Directive 193/31/EC dated 04/1999.

END OF CERTIFICATE

APPROVED