

Chemical resistance from HDPE membranes like DELTA® - MS, DELTA® - MS 20, DELTA® - TERRAXX, DELTA® - DRAIN, DELTA® - GEO DRAIN Quattro and DELTA- PT.

The table in this document summarises the data given in a number of chemical resistance tables at present in use in various countries, derived from both practical experience and test results.

Source: Carlowitz: "Kunststofftabellen-3 Auflage".

DELTA® dimpled membranes are made from the same HDPE raw material.

S- Satisfactory, U - Unsatisfactory, M - Marginal, N - Not known

Reagent	70 deg. F (21 °C)	140 deg. F (60 °C)
Acetic Acid 1-10%	S	S
Acetic Acid 10-60%	S	M
Acetic Acid 80-100%	S	M
Acetone	M	U
Acrylic Emulsions	S	S
Aluminum Chloride-Dilute	S	S
Aluminum Chloride Conc.	S	S
Aluminum Fluoride Conc.	S	S
Aluminum Sulfate Conc.	S	S
Alums (All Types) Conc.	S	S
Ammonia 100% Dry Gas	S	S
Ammonium Carbonate	S	S
Ammonium Chloride Sat'd	S	S
Ammonium Fluoride 20%	S	S
Ammonium Hydroxide 0.8S S.G.	S	S
Ammonium Metaphosphate Sat'd	S	S
Ammonium Nitrate Sat'd	S	S
Ammonium Persulfate Sat'd	S	S
Ammonium Sulfate Sat'd	S	S
Ammonium Sulfide Sat'd	S	S
Ammonium Thiocyanate Sat'd	S	S
Amyl Acetate	M	U
Amyl Alcohol 100%	S	S
Amyl Chloride 100%	N	U
Aniline 100%	S	N
Antimony Chloride	S	S

Aqua Regia	U	U
Barium Carbonate Sat'd	S	S
Barium Chloride	S	S
Barium Hydroxide	S	S
Barium Sulfate Sat'd	S	S
Barium Sulfide Sat'd	S	S
Beer	S	S
Benzene	M	U
Benzene Suffonic Acid	S	S
Bismuth Carbonate Sat'd	S	S
Bleach Lye 10%	S	S
Black Liquor	S	S
Borax Cold Sat'd	S	S
Boric Acid Dilute	S	S
Boric Acid Conc.	S	S
Bromic Acid 10%	S	S
Bromine Liquid 100%	M	U
butanediol 10%	S	S
butanediol 60%	S	S
butanediol 100%	S	S
butyl Alcohol 100%	S	S

Reagent	70 deg. F (21 °C)	140 deg. F (60 °C)
Calcium Bisulfide	S	S
Calcium Carbonate Sat'd	S	S
Calcium Chlorate Sat'd	S	S
Calcium Chloride Sat'd	S	S
Calcium Hydroxide	S	S
Calcium Hypochlorite RRGH	S	S
Calcium Nitrate 50%	S	S
Calcium Sulfate	S	S
Camphor Oil	N	U
Carbon Dioxide 100% Dry	S	S
Carbon Dioxide 100%Wet	S	S

Carbon Dioxide Cold Sat'd	S	S
Carbon Disulfide	N	U
Carbon Monoxide	S	S
Carbon Tetrachloride	M	U
Carbonic Acid	S	S
Castor Oil Conc.	S	S
Chlorine Dry Gas 100%	S	M
Chlorine Moist Gas	M	U
Chlorine Liquid	M	U
Chlorobenzene	M	U
Chloroform	M	U
Chlorosulfonic Acid 100%	M	U
Chrome Alum Sat'd	S	S
Chromic Acid 20%	S	S
Chromic Acid Up to 50%	S	S
Chromic Acid and Sulfuric Acid	S	M
Cider	S	S
Citric Acid Sat'd	S	S
Coconut Oil Alcohols	S	S
Cola Concentrates	S	S
Copper Chloride Sat'd	S	S
Copper Cyanide Sat'd	S	S
Copper Fluoride 2%	S	S
Copper Nitrate Sat'd	S	S
Copper Sulfate Dilute	S	S
Copper Sulfate Sat'd	S	S
Cottonseed Oil	S	S
Crude Oil	S	M
Cuprous Chloride Sat'd	S	S
Cychohexanol	S	S
Cyclohexanone	M	U
Detergents Synthetic	S	S
Developers, Photographic	S	S
Dextrin Sat'd	S	S
	S	S

Dextrose Sat'd		
Dibutylphthalate	S	M
Disodium Phosphate	S	S
Diazo Salts	S	S
Diethylene Glycol	S	S
Diglycolic Acid	S	S
Dimethylamine	M	U
Emulsions, Photographic	S	S
Ethyl Acetate 100%	M	U
Ethyl Alcohol 100%	S	S
Ethyl Alcohol 35%	S	S
Ethyl butyrate	M	U
Ethyl Chloride	M	U
Ethyl Ether	U	U
Ethylene Chloride	U	U
Ethylene Chlorohydrin	U	U
Ethylene Dichloride	M	U
Ethylene Glycol	S	S
Reagent	70 deg. F	140 deg. F
	(21 °C)	(60 °C)
Ferric Chloride Sat'd	S	S
Ferric Nitrate Sat'd	S	S
Ferrous Chloride Sat'd	S	S
Ferrous Sulfate	S	S
Fish Solubles	S	S
Fluoboric Acid	S	S
Fluorine	S	U
Fluosilicic Acid 32%	S	S
Fluosilicic Acid Conc.	S	S
Formaldehyde 40%	S	N
Formic Acid 0-20%	S	S
Formic Acid 20-50%	S	S
Formic Acid 100%	S	S
	S	S

Fructose Sat'd		
Fruit Pulp	S	S
Fuel Oil	S	U
Furfural 100%	M	U
Furfuryl Alcohol	M	U
Gallic Acid Sat'd	S	S
Gas Liquids	S	M
Gasoline	M	U
Gin	S	U
Glucose	S	S
Glycerine	S	S
Glycol	S	S
Glycolic Acid 30%	S	S
Grape Sugar Sat'd Aq.	S	S
Hexanol, Tert.	S	S
Hydrobromic Acid 50j/O	S	S
Hydrocyanic Acid Sat'd	S	S
HydrochloricAcid 10%	S	S
Hydrochloric Acid 30%	S	S
Hydrochloric Acid 35%	S	S
Hydrochloric Acid Conc.	S	S
Hydrofluoric Acid 40%	S	S
Hydrofluoric Acid 60%	S	S
Hydrofluoric Acid 75%	S	S
Hydrogen 100%	S	S
Hydrogen Bromide 10%	S	S
Hydrogen Chloride Gas Dry	S	S
Hydrogen Peroxide 30%	S	S
Hydrogen Peroxide 90%	S	M
Hydrogen Phosphide 100%	S	S
Hydroquinone	S	S
Hydrogen Sulfide	S	S
Hypochlorus Acid Conc.	S	S
Inks	S	S
	S	U

Lodine (Alc. Sol.) Conc.		
Lactic Acid 10%	S	S
Lactic Acid 90j/O	S	S
Latex	S	S
Lead Acetate Sat'd	S	S
Lube Oil	S	M
Magnesium Carbonate Sat'd	S	S
Magnesium Chloride Sat'd	S	S
Magnesium Hydroxide Sat'd	S	S
Magnesium Nitrate Sat'd	S	S
Magnesium Sulfate Sat'd	S	S
Mercuric Chloride Sat'd	S	S
Mercuric Cyanide Sat'd	S	S
Mercurous Nitrate Sat'd	S	S
Mercury	S	S
Methyl Alcohol 100%	S	S
Methyl Bromide	M	U
Methyl Chloride	M	U
Methyl Ethyl Ketone 100%	M	U
Methylsulfuric Acid	S	S
Methylene Chloride 100%	M	U
Milk	S	S
Mineral Oils	S	U
Molasses Comm.	S	S
Reagent	70 deg. F	140 deg. F
	(21 °C)	(60 °C)
Nickel Chloride Sat'd	S	S
Nickel Nitrate Conc.	S	S
Nickel Sulfate Sat'd	S	S
Nicotine Dilute	S	S
Nicotinic Acid	S	S
Nitric Acid 0-30%	S	S
Nitric Acid 30-50%	S	M
Nitric Acid 70%	S	M

Nitric Acid 95-98%	U	U
Nitrobenzene 100%	U	U
Octyl Cresol	S	U
Oils and Fats	S	M
Oleic Acid Conc.	S	U
Oleum Conc.	U	U
Orange Extract	S	S
Oxalic Acid Dilute	S	S
Oxalic Acid Sat'd	S	S
Ozone 100%	S	U
PerchloneAcid 10%	S	S
Petroleum Ether	U	U
Phenol 90%	U	U
Phosphoric Acid Up to 30%	S	S
Phosphoric Acid Over 30%	S	S
Phosphoric Acid 90%	S	S
Phosphorous (Yellow) 100%	S	N
Phosphorus Pentoxide 100%	S	N
Photographic Solutions	S	S
Pickling Baths		
• Sulfuric Acid	S	S
• Hydrochloric Acid	S	S
• Sulfuric-Nitric	S	U
Plating Solutions		
• Brass	S	S
• Cadmium	S	S
• Chromium	N	N
• Copper	S	S
• Gold	S	S
• Indium	S	S

Bauverbundfolien

• Lead	S	S
• Nickel	S	S
• Rhodium	S	S
• Silver	S	S
• Tin	S	S
• Zinc	S	S
Potassium Bicarbonate Sat'd	S	S
Potassium Borate 1%	S	S
Potassium Bromate 10%	S	S
Potassium Bromide Sat'd	S	S
Potassium Carbonate	S	S
Potassium Chlorate Sat'd	S	S
Potassium Chloride Sat'd	S	S
Potassium Chromate 40%	S	S
Potassium Cyanide Sat'd	S	S
Potassium Dichromate 40%	S	S
Potassium Ferri/Ferro Cyanide Sat'd	S	S
Potassium Fluoride	S	S
Potassium Hydroxide 20%	S	S
Potassium Hydroxide Conc.	S	S
Potassium Nitrate Sat'd	S	S
Potassium Perborate Sat'd	S	S
Potassium Perchlorate 10%	S	S
Potassium Sulfate Conc.	S	S
Potassium Sulfide Conc.	S	S
Potassium Sulfite Conc.	S	S
Potassium Persulfate Satd	S	S
Propargyl Alcohol	S	S
Propyl Alcohol	S	S
Propylene Dichloride 100%	U	U
Propylene Glycol	S	S
Rayon Coagulating Bath	S	S

Reagent	70 deg.F (21 °C)	140 deg.F (60 °C)
Sea Water	S	S
Selenic Acid	S	S
Shortening	S	S
Silicic Acid	S	S
Silver Nitrate Sol.	S	S
Soap Solution Any Conc'n	S	S
Sodium Acetate Sat'd	S	S
Sodium Benzoate 35%	S	S
Sodium Bicarbonate Sat'd	S	S
Sodium Bisulfate Sat'd	S	S
Sodium Bisulfite Sat'd	S	S
Sodium Borate	S	S
Sodium Bromide Dilute Sol.	S	S
Sodium Carbonate Con.	S	S
Sodium Carbonate	S	S
Sodium Chlorate Sat'd.	S	S
Sodium Chloride Sat'd	S	S
Sodium Cyanide	S	S
Sodium Dichromate Sat'd	S	S
Sodium Ferrocyanide	S	S
Sodium Ferrocyanide Sat'd	S	S
Sodium Fluoride Sat'd	S	S
Sodium Hydroxide Conc.	S	S
Sodium Hypochlorite	S	S
Sodium Nitrate	S	S
Sodium Sulfate	S	S
Sodium Sulfide 25%	S	S
Sodium Sulfide Sat'd Sol.	S	S
Sodium Sulfite Sat'd	S	S
Stannous Chloride Sat'd	S	S
Stannic Chloride Sat'd	S	S
Starch Solution SaUd	S	S
Stearic Acid 100%	S	S
Sulfuric Acid 0-50%	S	S
Sulfuric Acid 70%	S	M

Bauverbundfolien

Sulfuric Acid 80%	S	U
Sulfuric Acid 96%	M	U
Sulfuric Acid 98%	M	U
Sulfuric Acid, Fuming	U	U
Sulfurous Acid	S	S
Tallow S M Tannic Acid 10%	S	S
Tanning Extracts Comm.	S	S
Tartaric Acid Sat'd	N	N
Tetrahydrofurane	N	U
Titanium Tetrachloride Sat'd	N	U
Toluene	M	U
Transformer Oil	S	M
Trisodium Phosphate Sat'd	S	S
Trichloroethylene	U	U
Urea Up to 30%	S	S
Urine	S	S
Vinegar Comm.	S	S
Vanilla Extract	S	S
Wetting Agents	S	S
Whiskey	S	N
Wines	S	S
Xylene	M	U
Yeast	S	S
Zinc Chloride Sat'd	S	S
Zinc Sulfate Sat'd	S	S

S- Satisfactory, U - Unsatisfactory, M - Marginal, N - Not known